



Declaration	of	Conformity -	Ref.No	445165
-------------	----	--------------	---------------	--------

In compliance with the Construction Products Regulation and The Construction Products (Amendment etc.) (EU Exit) Regulations 2020.

1.	Identification code of product-type	PremiumBoard P5, FormBoard P5 – 445165
2.	Intended use	Load-bearing boards for use in humid conditions
3.	Manufacturer	Pfleiderer Deutschland GmbH, Ingolstädter Str. 51, D – 92318 Neumarkt
4.	Authorised representative	not relevant
5.	System of assessment and verification	System 2+
6.	Assessment of performance	This Certificate attests that all provisions concerning the assessment and verification of constancy of performance described in the EN: BS EN 13986:2004 + A1 2015 under system 2+ for the performances set out in the certificate UK 0836-CPR-22/F6272 are applied and that the factory production control fulfils all the prescribed requirements for these performances.
7.	European Technical Assessment	not relevant



8. Declared performance

-	Thickness	≤ 8.9 mm	> 8.9 mm to ≤ 10 mm	to	to	to	> 25 mm to ≤ 32 mm	to		Harmonised technical
Essential characteristics/main features	Unit	Declared performance s								pecification
Strength, tension (ft)	N/mm ²	9.4 8.5 7.4 6.6 5.6							EN	
Strength, compression (fc)	N/mm ²	12.7			11.8	10.3	9.8	8.5	7.8	13986:2004 +A1:2015
Strength, bending (fm)	N/mm ²	15.0		-	13.3	11.7	10.0	8.3	7.5	TA1.2015
Stiffness, panel shear (fv)	N/mm ²	7.0		-	6.5	5.9	5.2	4.8	4.4	
Stiffness, planar shear (fr)	N/mm ²	1.9			1.7	1.5	1.3	1.2	1.0	
Punching shear as point load strenght		NPD								
Punching shear as point load stiffness		NPD								1
Racking resistance		NPD								
Impact resistance		NPD]
Reaction to fire		E		according Gross dens			lent on end	d use (Thio	ckness: ≥	
Water vapour permeability, wet cup $\boldsymbol{\mu}$		15								-
Water vapour permeability, dry cup µ		50								
Class, formaldehyde release		E1 E05								
Release (Content), pentachlorophenol (PCP)	mg/kg	< 3								
Airborne sound insulation (surface mass)		NPD								
Sound Absorption frequency range 250 Hz to 500 Hz		0.1								
Sound Absorption frequency range 1000 Hz to 2000 Hz		0.25								
Thermal conductivity (density)	W/(mK)	0.12								1
Embedment strength		NPD								
Air permeability		NPD								
Internal bond	N/mm ²	0.45				0.4	0.35	0.3	0.25	
Swelling in thickness, 24 h	%	13		11	10			9]
Internal bond after boil test	N/mm ²	0.15			0.14	0.12	0.11	0.1	0.09	
Factor of modification (kmod)		NPD								
Factor of distortion (kdef)		NPD								

9. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 8. This Declaration of Conformity is issued under the sole responsibility of the manufacturer identified in point 3.

Signed for and on behalf of the manufacturer by:

Date of issue: 2024-05-07

i. V. Claus Seemann Head of productmanagement core materials (Document was created electronically and is therefore valid without signature!)

> NPD: performance not defined Technical values refer to the core material