

Technical data

PerformBoard raw Dfl P4

| | |
|-------------------------------------|-----------|
| Tolerance on thickness | ± 0.3 mm |
| Tolerance on length (EN 324-1) | ± 5 mm |
| Tolerance on width (EN 324-1) | ± 5 mm |
| Längen- / Breitentoleranz Zuschnitt | ± 2.5 mm |
| Straightness of edges (EN 324-2) | 1.5 mm/m |
| Squareness (EN 324-2) | 2 mm/m |
| Moisture content (EN 322) | 9 % ± 4 % |
| Formaldehyde emission class | E1 E05 |

| Property | Test method | Unit | Requirement |
|-------------------------------|-------------|-------------------|---|
| | | | Thickness / Range of thickness (mm, nominal dimension) |
| | | | > 32 to ≤ 40 |
| Mean density | EN 323 | kg/m ³ | 620 – 600 |
| Bending strength | EN 310 | N/mm ² | 9 |
| Bending modulus of elasticity | EN 310 | N/mm ² | 1,500 |
| Internal bond | EN 319 | N/mm ² | 0.2 |
| Swelling in thickness, 24 h | EN 317 | % | 14 |

© Copyright 2024 Pfeiderer Deutschland GmbH

This information has been compiled with the greatest care. Nevertheless we can assume no liability for the correctness, completeness and up-to-date-ness of this information. Colour deviations caused by the printing technology are possible. In view of the ongoing further development and adaptation of our products, possible amendments to the relevant standards, laws and regulations, our technical data sheets and product documentation expressly do not constitute a legally binding assurance of the properties described there. In particular no guarantee of suitability for a concrete application can be derived. It is therefore the personal responsibility of the individual user in all cases to check the processing and suitability of the products described in this document for the intended application in advance, and to take into consideration the legal framework and the respective state-of-the-art. We furthermore expressly draw attention to the applicability of our General Terms and Conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com