

High-quality multi-layer-lacquering

StyleBoard MDF black

Raw, untreated

April 2025

Technical data PrimeBoard XTreme High Gloss MDF black Natural

fa:

Easy to use and machine

Natural, raw, decorative black through-dyed melamine faced medium-density fibreboard (MDF), with high quality and innovative high gloss multi-layer coating, made up of a permanently elastic functional layer, for vertical applications.

Easy care

Applications



Properties



Certificates



Specification				Unit	Test standard
Nominal thickness	16	19	25	mm	
Tolerance on thickness	+0.5/-0.3	+0.5/-0.3	±0,5	mm	EN 14323
Length- and width tolerance		± 5		mm	EN 14323
Flatness	≤ 2 ¹⁾			mm/m	EN 14323
Edge damage	<u>≤ 10</u>			mm	EN 14323
Resistance to scratching	≥ 2.5			N	in accordance with EN 15186 / Method B
Resistance to microscratching	1				DIN CEN/TS 16611, IHD-W-466 / Method A
Cross-cut test	≤ 1			Specific value	EN ISO 2409
Chemical resistance	1B			Durabili- ty class	DIN 68861-1
Surface gloss	≥ 90 / 60°				EN 13722
Behavior at abrasion	2A			Durabili- ty class	DIN 68861-2
Resistance to colour change in xenon arc light	min. 4 Grey Scale Grade min. 6 Blue Wool Standard				EN 15187
Resistance to cracking	5			Rating	EN 14323
Behaviour in dry heat	7D (70 °C)			Durabili- ty class	DIN 68861-7
Behaviour in humid heat	8B (70 °C)			Durabili- ty class	DIN 68861-8
Surface defects	1.0 mm ² and detected fro angle of about 30° dur Max. 1 fault per m ² is pe	om an observation distanding the evaluation of the s	er of defects allowed per		
Reaction to fire	normally flammable				
Reaction to fire (Euroclass)	D-s2,d0				EN 13986 (CWFT) dependent on end use
Formaldehyde emission class	E1 E05 TSCA Title VI				EN 717-1

+49 (0) 91 81 28 48 0 +49 (0) 91 81 28 48 2 info@pfleiderer.com www.pfleiderer.com

phone

Fax



April 2025

Technical data PrimeBoard XTreme High Gloss MDF black Natural

Specification				Unit	Test standard
Nominal thickness	16	19	25	mm	
Mean density	770 ²⁾			kg/m³	EN 323
Flexural strength	27 ²⁾			N/mm ²	EN 310
Modulus of elasticity (bending stiffness)		N/mm²	EN 310		
Internal bond		N/mm²	EN 319		
Thickness swell (24 h)	≤ 12 ²⁾	≤ 12 ²⁾	≤ 10 ²⁾	%	EN 317

¹⁾ If symmetrical decor structure

²⁾ Core material

Additional information

Product standard	in accordance with EN 14322				
Areas of application	 Shop design / product presentation, exclusive interior and project fixtures and fittings, living room and bedroom furniture / sliding doors, bathroom furniture and kitchen fronts. 				
Core material	 StyleBoard MDF black Decorative black through-dyed medium-density fibreboard (MDF), with a uniform structure. 				
Product safety	 This product follows the REACH regulation EC 1907/2006 an article. Following Article 7 it does not need to be registered. We manufacture the panels without the use of organohalogens, heavy metals, preservatives, wood protectors or organic solvents. 				
Special	 The lacquering can be applied on one or both sides. With one sided lacquering, the reverse is raw / untreated. The main quality features of PrimeBoard XTreme are listed in this document. Individually requested properties not listed here can, if necessary, be answered on request in accordance with the relevant standards and test procedures. Due to the industrial manufacturing process and despite state-of-the-art production technology, it is not possible to produce a completely faultless surface, minor imperfections and surface irregularities are therefore permissible. To protect the high quality surface Pfleiderer delivers these surface textures with a protective foil. The protective foil must be removed as soon as possible after processing – but at the latest within 6 months after delivery – to ensure residue-free removal of the foil. In addition, foiled boards must not be exposed to direct sunlight (UV radiation). We recommend use in indoor areas with normal climatic conditions, i.e. with a relative humidity of 40 – 60 % and natural daylight. In buildings with ventilation technology, the normal climate must be permanently maintained by means of appropriate ventilation. All stated technical values apply only in moderate climate zones with room temperatures of max. 35°C. Under unfavourable climatic conditions, such as temperatures above 35°C, complete darkness and very high humidity, coated products may develop a slight dark yellowing. This is reversible by UV irradiation, but a complete restoration of the original colour is not guaranteed. We accept no liability for this process and the resulting colour changes. Due to the use of a natural wood-based material, the appearance of the panel can vary. Such deviations are due to the desired character of the product As is usual with natural products each board is unique. 				
Disposal	 are due to the desired character of the product. As is usual with natural products, each board is unique. PrimeBoard XTreme is classified in waste wood class A2. The known disposal regulations regarding material and energy recovery apply. 				
Note	 FSC certification or PEFC certification available on request. FSC license code: FSC[®] C011773 PEFC license code: PEFC/04-32-0828 				
Colour and surface match	 Decor, structure and core board all influence the final appearance of the end product. Due to the product-specific differences in production technologies, even identical decor/structure/core board combinations can result in slight optical and tactile deviations across different product groups and formats. Such deviations do not constitute a defect. The choice of surface structure in particular has a significant influence on the visual impression, the tactile perception as well as the technical characteristics of the product. Thus, the overall impression of a decor can change almost completely depending on the surface structure. Furthermore, mechanical influences on the product surface can lead to a higher contrast optical perception with dark decors. To ensure that you always achieve the best results with our products and to clarify any deviations in advance, we will be happy to advise you individually. 				

Fax



April 2025

Technical data

PrimeBoard XTreme High Gloss MDF black Natural

Further information on products, formats and decor/structure combinations is available at www.pfleiderer.com

Fax

© Copyright 2025 Pfleiderer Deutschland GmbH

This information is issued with great care. We do not however accept any responsibility for the accuracy, completeness and timeliness. There may be slight colour differences between the printed brochure image and the actual design.

Due to the continuous development and modification of our products, possible changes to the relevant standards, laws and regulations, our technical data sheets and product documents expressly do not represent a legally binding guarantee of the properties specified therein. In particular, no suitability for a specific purpose can be derived from this information. It is therefore the personal responsibility of the individual user to check the processing and suitability of the products described in this document for the intended use and to take into account the legal framework and the current state of the art. Furthermore, we expressly refer to the validity of our general terms and conditions.

You can find our general terms and conditions on our webpage: www.pfleiderer.com

Pfleiderer Deutschland GmbH
Ingolstädter Str. 51
92318 Neumarkt
Germany

+49 (0) 91 81 28 48 0 phone +49 (0) 91 81 28 48 2 info@pfleiderer.com www.pfleiderer.com